

Ultra-Drum Tourniquet

Chemical Compatibility Guide

CHEMICAL	COMPATIBILITY
Acetaldehyde	A - Excellent
Acetamide	A - Excellent
Acetate Solvent	A - Excellent
Acetic Acid	A - Excellent
Acetic Acid 20%	A - Excellent
Acetic Acid 80%	A - Excellent
Acetic Acid, Glacial	B - Good
Acetic Anhydride	B - Good
Acetone	A - Excellent
Acetyl Bromide	N/A
Acetyl Chloride (dry)	D - Poor
Acetylene	A - Excellent
Acrylonitrile	D - Poor
Adipic Acid	A ² - Excellent
Alcohols: Amyl	A - Excellent
Alcohols: Benzyl	B - Good
Alcohols: Butyl	A ² - Excellent
Alcohols: Diacetone	A - Excellent
Alcohols: Ethyl	A - Excellent
Alcohols: Hexyl	C - Fair
Alcohols: Isobutyl	A - Excellent
Alcohols: Isopropyl	A - Excellent
Alcohols: Methyl	A - Excellent
Alcohols: Octyl	A - Excellent
Alcohols: Propyl	A - Excellent
Aluminum Chloride	A - Excellent
Aluminum Chloride 20%	A - Excellent
Aluminum Fluoride	A - Excellent
Aluminum Hydroxide	A - Excellent
Aluminum Nitrate	A ² - Excellent
Aluminum Potassium Sulfate 10%	A - Excellent
Aluminum Potassium Sulfate 100%	A - Excellent
Aluminum Sulfate	A - Excellent
Alums	A ¹ - Excellent
Amines	B - Good
Ammonia 10%	A - Excellent
Ammonia Nitrate	A - Excellent
Ammonia, anhydrous	A - Excellent
Ammonia, liquid	A - Excellent
Ammonium Acetate	A - Excellent
Ammonium Bifluoride	A ² - Excellent

CHEMICAL	COMPATIBILITY
Ammonium Carbonate	A - Excellent
Ammonium Caseinate	N/A
Ammonium Chloride	A - Excellent
Ammonium Hydroxide	A - Excellent
Ammonium Nitrate	A - Excellent
Ammonium Oxalate	A - Excellent
Ammonium Persulfate	B - Good
Ammonium Phosphate, Dibasic	A - Excellent
Ammonium Phosphate, Monobasic	A - Excellent
Ammonium Phosphate, Tribasic	A - Excellent
Ammonium Sulfate	A - Excellent
Ammonium Sulfite	A ¹ - Excellent
Ammonium Thiosulfate	A ¹ - Excellent
Amyl Acetate	A - Excellent
Amyl Alcohol	A - Excellent
Amyl Chloride	D - Poor
Aniline	B - Good
Aniline Hydrochloride	B - Good
Antifreeze	A - Excellent
Antimony Trichloride	B ¹ - Good
Aqua Regia (80% HCl, 20% HNO ₃)	C - Fair
Arochlor 1248	B - Good
Aromatic Hydrocarbons	D - Poor
Arsenic Acid	A ² - Excellent
Arsenic Salts	N/A
Asphalt	D - Poor
Barium Carbonate	A - Excellent
Barium Chloride	A - Excellent
Barium Cyanide	A - Excellent
Barium Hydroxide	A - Excellent
Barium Nitrate	A - Excellent
Barium Sulfate	A - Excellent
Barium Sulfide	A - Excellent
Beer	A - Excellent
Beet Sugar Liquids	A - Excellent
Benzaldehyde	A - Excellent
Benzene	D - Poor
Benzene Sulfonic Acid	D - Poor
Benzoic Acid	D - Poor
Benzol	D - Poor
Benzonitrile	N/A
Benzyl Chloride	D - Poor
Bleaching Liquors	A - Excellent
Borax (Sodium Borate)	A - Excellent
Boric Acid	A - Excellent

CHEMICAL	COMPATIBILITY
Brewery Slop	N/A
Bromine	D - Poor
Butadiene	C - Fair
Butane	D - Poor
Butanol (Butyl Alcohol)	A ² - Excellent
Butter	A - Excellent
Buttermilk	A ¹ - Excellent
Butyl Amine	N/A
Butyl Ether	D - Poor
Butyl Phthalate	B ² - Good
Butylacetate	B - Good
Butylene	D - Poor
Butyric Acid	B - Good
Calcium Bisulfate	A - Excellent
Calcium Bisulfide	C - Fair
Calcium Bisulfite	D - Poor
Calcium Carbonate	A - Excellent
Calcium Chlorate	A - Excellent
Calcium Chloride	A - Excellent
Calcium Hydroxide	A - Excellent
Calcium Hypochlorite	B ¹ - Good
Calcium Nitrate	A ² - Excellent
Calcium Oxide	A - Excellent
Calcium Sulfate	A - Excellent
Calgon	A - Excellent
Cane Juice	A - Excellent
Carbolic Acid (Phenol)	B - Good
Carbon Bisulfide	D - Poor
Carbon Dioxide (dry)	B - Good
Carbon Dioxide (wet)	B - Good
Carbon Disulfide	D - Poor
Carbon Monoxide	A - Excellent
Carbon Tetrachloride	D - Poor
Carbon Tetrachloride (dry)	B ¹ - Good
Carbon Tetrachloride (wet)	D - Poor
Carbonated Water	N/A
Carbonic Acid	B - Good
Catsup	A - Excellent
Chloric Acid	N/A
Chlorinated Glue	B - Good
Chlorine (dry)	A - Excellent
Chlorine Water	C - Fair
Chlorine, Anhydrous Liquid	B - Good
Chloroacetic Acid	B - Good
Chlorobenzene (Mono)	D - Poor
Chlorobromomethane	B - Good

CHEMICAL	COMPATIBILITY
Chloroform	D - Poor
Chlorosulfonic Acid	D - Poor
Chocolate Syrup	A - Excellent
Chromic Acid 10%	C - Fair
Chromic Acid 30%	B - Good
Chromic Acid 5%	A - Excellent
Chromic Acid 50%	B - Good
Chromium Salts	N/A
Cider	A - Excellent
Citric Acid	A - Excellent
Citric Oils	B - Good
Cloroxr (Bleach)	B - Good
Coffee	A - Excellent
Copper Chloride	A - Excellent
Copper Cyanide	A - Excellent
Copper Fluoborate	N/A
Copper Nitrate	N/A
Copper Sulfate >5%	A - Excellent
Copper Sulfate 5%	A - Excellent
Cream	N/A
Cresols	D - Poor
Cresylic Acid	D - Poor
Cupric Acid	A ² - Excellent
Cyanic Acid	N/A
Cyclohexane	D - Poor
Cyclohexanone	B - Good
Detergents	A - Excellent
Diacetone Alcohol	A - Excellent
Dichlorobenzene	D - Poor
Dichloroethane	N/A
Diesel Fuel	D - Poor
Diethyl Ether	D - Poor
Diethylamine	B - Good
Diethylene Glycol	A ² - Excellent
Dimethyl Aniline	B ² - Good
Dimethyl Formamide	B - Good
Diphenyl	D - Poor
Diphenyl Oxide	D - Poor
Dyes	N/A
Epsom Salts (Magnesium Sulfate)	A - Excellent
Ethane	D - Poor
Ethanol	A - Excellent
Ethanolamine	B - Good
Ether	C - Fair
Ethyl Acetate	B - Good

CHEMICAL	COMPATIBILITY
Ethyl Benzoate	N/A
Ethyl Chloride	A - Excellent
Ethyl Ether	D - Poor
Ethyl Sulfate	N/A
Ethylene Bromide	C - Fair
Ethylene Chloride	D - Poor
Ethylene Chlorohydrin	B - Good
Ethylene Diamine	A - Excellent
Ethylene Dichloride	C - Fair
Ethylene Glycol	A - Excellent
Ethylene Oxide	C - Fair
Fatty Acids	D - Poor
Ferric Chloride	A - Excellent
Ferric Nitrate	A - Excellent
Ferric Sulfate	A - Excellent
Ferrous Chloride	N/A
Ferrous Sulfate	A - Excellent
Fluoboric Acid	A ² - Excellent
Fluorine	A ¹ - Excellent
Fluosilicic Acid	A ² - Excellent
Formaldehyde 100%	A - Excellent
Formaldehyde 40%	A - Excellent
Formic Acid	A - Excellent
Freon 113	D - Poor
Freon 12	B - Good
Freon 22	A - Excellent
Freon TF	D - Poor
Freonr 11	D - Poor
Fruit Juice	N/A
Fuel Oils	D - Poor
Furan Resin	C - Fair
Furfural	D - Poor
Gallic Acid	B - Good
Gasoline (high-aromatic)	D - Poor
Gasoline, leaded, ref.	D - Poor
Gasoline, unleaded	D - Poor
Gelatin	A - Excellent
Glucose	A - Excellent
Glue, P.V.A.	A - Excellent
Glycerin	A - Excellent
Glycolic Acid	A - Excellent
Gold Monocyanide	N/A
Grape Juice	A - Excellent
Grease	D - Poor
Heptane	D - Poor
Hexane	D - Poor

CHEMICAL	COMPATIBILITY
Honey	A - Excellent
Hydraulic Oil (Petro)	D - Poor
Hydraulic Oil (Synthetic)	A - Excellent
Hydrazine	A - Excellent
Hydrobromic Acid 100%	A - Excellent
Hydrobromic Acid 20%	A - Excellent
Hydrochloric Acid 100%	D - Poor
Hydrochloric Acid 20%	A - Excellent
Hydrochloric Acid 37%	C - Fair
Hydrochloric Acid, Dry Gas	N/A
Hydrocyanic Acid	B - Good
Hydrocyanic Acid (Gas 10%)	A - Excellent
Hydrofluoric Acid 100%	D - Poor
Hydrofluoric Acid 20%	D - Poor
Hydrofluoric Acid 50%	D - Poor
Hydrofluoric Acid 75%	C - Fair
Hydrofluosilicic Acid 100%	A - Excellent
Hydrofluosilicic Acid 20%	A - Excellent
Hydrogen Gas	A - Excellent
Hydrogen Peroxide 10%	A - Excellent
Hydrogen Peroxide 100%	D - Poor
Hydrogen Peroxide 30%	B - Good
Hydrogen Peroxide 50%	B - Good
Hydrogen Sulfide (aqua)	B - Good
Hydrogen Sulfide (dry)	B - Good
Hydroquinone	D - Poor
Hydroxyacetic Acid 70%	A - Excellent
Ink	N/A
Iodine	B - Good
Iodine (in alcohol)	A - Excellent
Iodoform	A - Excellent
Isooctane	D - Poor
Isopropyl Acetate	B - Good
Isopropyl Ether	D - Poor
Isotane	N/A
Jet Fuel (JP3, JP4, JP5)	D - Poor
Kerosene	D - Poor
Ketones	A - Excellent
Lacquer Thinners	D - Poor
Lacquers	D - Poor
Lactic Acid	A - Excellent
Lard	D - Poor
Latex	A - Excellent
Lead Acetate	A - Excellent
Lead Nitrate	A ² - Excellent

CHEMICAL	COMPATIBILITY
Lead Sulfamate	A - Excellent
Ligroin	D - Poor
Lime	D - Poor
Linoleic Acid	D - Poor
Lithium Chloride	A ¹ - Excellent
Lithium Hydroxide	N/A
Lubricants	D - Poor
Lye: Ca(OH) ₂ Calcium Hydroxide	A - Excellent
Lye: KOH Potassium Hydroxide	A ² - Excellent
Lye: NaOH Sodium Hydroxide	B ¹ - Good
Magnesium Bisulfate	N/A
Magnesium Carbonate	A - Excellent
Magnesium Chloride	A - Excellent
Magnesium Hydroxide	A - Excellent
Magnesium Nitrate	A - Excellent
Magnesium Oxide	N/A
Magnesium Sulfate (Epsom Salts)	A - Excellent
Maleic Acid	D - Poor
Maleic Anhydride	D - Poor
Malic Acid	D - Poor
Manganese Sulfate	A ² - Excellent
Mash	A - Excellent
Mayonnaise	N/A
Melamine	A - Excellent
Mercuric Chloride (dilute)	A ¹ - Excellent
Mercuric Cyanide	A ¹ - Excellent
Mercurous Nitrate	A ¹ - Excellent
Mercury	A - Excellent
Methane	D - Poor
Methanol (Methyl Alcohol)	A - Excellent
Methyl Acetate	B - Good
Methyl Acetone	A ¹ - Excellent
Methyl Acrylate	B - Good
Methyl Alcohol 10%	A - Excellent
Methyl Bromide	D - Poor
Methyl Butyl Ketone	A ¹ - Excellent
Methyl Cellosolve	B ² - Good
Methyl Chloride	D - Poor
Methyl Dichloride	D - Poor
Methyl Ethyl Ketone	A ² - Excellent
Methyl Ethyl Ketone Peroxide	D - Poor
Methyl Isobutyl Ketone	B ¹ - Good
Methyl Isopropyl Ketone	C ¹ - Fair
Methyl Methacrylate	D - Poor
Methylamine	A ¹ - Excellent

CHEMICAL	COMPATIBILITY
Methylene Chloride	C ¹ - Fair
Milk	A - Excellent
Mineral Spirits	D - Poor
Molasses	A ¹ - Excellent
Monochloroacetic acid	C - Fair
Monoethanolamine	B - Good
Morpholine	D - Poor
Motor oil	D - Poor
Mustard	A - Excellent
Naphtha	D - Poor
Naphthalene	D - Poor
Natural Gas	D - Poor
Nickel Chloride	A ¹ - Excellent
Nickel Nitrate	A ² - Excellent
Nickel Sulfate	A ¹ - Excellent
Nitrating Acid (<15% HNO3)	N/A
Nitrating Acid (>15% H2SO4)	A ¹ - Excellent
Nitrating Acid (S1% Acid)	N/A
Nitrating Acid (S15% H2SO4)	N/A
Nitric Acid (20%)	A ¹ - Excellent
Nitric Acid (50%)	D - Poor
Nitric Acid (5-10%)	A ¹ - Excellent
Nitric Acid (Concentrated)	D - Poor
Nitrobenzene	B ¹ - Good
Nitrogen Fertilizer	N/A
Nitromethane	B ² - Good
Nitrous Acid	A - Excellent
Nitrous Oxide	A - Excellent
Oils: Aniline	B - Good
Oils: Anise	N/A
Oils: Bay	N/A
Oils: Bone	N/A
Oils: Castor	B - Good
Oils: Cinnamon	N/A
Oils: Citric	B - Good
Oils: Clove	N/A
Oils: Coconut	D - Poor
Oils: Cod Liver	A - Excellent
Oils: Corn	C - Fair
Oils: Cottonseed	D - Poor
Oils: Creosote	D - Poor
Oils: Diesel Fuel (20, 30, 40, 50)	D - Poor
Oils: Fuel (1, 2, 3, 5A, 5B, 6)	D - Poor
Oils: Ginger	A - Excellent
Oils: Hydraulic Oil (Petro)	D - Poor
Oils: Hydraulic Oil (Synthetic)	A - Excellent

CHEMICAL	COMPATIBILITY
Oils: Lemon	D - Poor
Oils: Linseed	D - Poor
Oils: Mineral	D - Poor
Oils: Olive	D - Poor
Oils: Orange	N/A
Oils: Palm	A - Excellent
Oils: Peanut	D - Poor
Oils: Peppermint	N/A
Oils: Pine	D - Poor
Oils: Rapeseed	A - Excellent
Oils: Rosin	N/A
Oils: Sesame Seed	N/A
Oils: Silicone	A - Excellent
Oils: Soybean	C - Fair
Oils: Sperm (whale)	N/A
Oils: Tanning	N/A
Oils: Transformer	D - Poor
Oils: Turbine	A - Excellent
Oleic Acid	B - Good
Oleum 100%	D - Poor
Oleum 25%	D - Poor
Oxalic Acid (cold)	A - Excellent
Ozone	A - Excellent
Palmitic Acid	B ¹ - Good
Paraffin	D - Poor
Pentane	D - Poor
Perchloric Acid	B - Good
Perchloroethylene	D - Poor
Petrolatum	A - Excellent
Petroleum	D - Poor
Phenol (10%)	B - Good
Phenol (Carbolic Acid)	B - Good
Phosphoric Acid (>40%)	B - Good
Phosphoric Acid (crude)	B - Good
Phosphoric Acid (molten)	N/A
Phosphoric Acid (S40%)	B - Good
Phosphoric Acid Anhydride	N/A
Phosphorus	N/A
Phosphorus Trichloride	A ¹ - Excellent
Photographic Developer	B - Good
Photographic Solutions	A ¹ - Excellent
Phthalic Acid	A ¹ - Excellent
Phthalic Anhydride	A - Excellent
Picric Acid	B - Good
Plating Solutions, Antimony Plating 130°F	N/A

CHEMICAL	COMPATIBILITY
Plating Solutions, Arsenic Plating 110°F	N/A
Plating Solutions, Brass Plating: High- Speed Brass Bath 110°F	N/A
Plating Solutions, Brass Plating: Regular Brass Bath 100°F	N/A
Plating Solutions, Bronze Plating: Cu- Cd Bronze Bath R.T.	A - Excellent
Plating Solutions, Bronze Plating: Cu- Sn Bronze Bath 160°F	A - Excellent
Plating Solutions, Bronze Plating: Cu- Zn Bronze Bath 100°F	N/A
Plating Solutions, Cadmium Plating: Cyanide Bath 90°F	N/A
Plating Solutions, Cadmium Plating: Fluoborate Bath 100°F	N/A
Plating Solutions, Chromium Plating: Barrel Chrome Bath 95°F	N/A
Plating Solutions, Chromium Plating: Black Chrome Bath 115°F	N/A
Plating Solutions, Chromium Plating: Fluoride Bath 130°F	N/A
Plating Solutions, Chromium Plating: Fluosilicate Bath 95°F	N/A
Plating Solutions, Chromium Plating: Chromic-Sulfuric Bath 130°F	N/A
Plating Solutions, Copper Plating (Acid): Copper Fluoborate Bath 120°F	N/A
Plating Solutions, Copper Plating (Acid): Copper Sulfate Bath R.T.	N/A
Plating Solutions, Copper Plating (Cyanide): Copper Strike Bath 120°F	N/A
Plating Solutions, Copper Plating (Cyanide): High-Speed Bath 180°F	N/A
Plating Solutions, Copper Plating (Cyanide): Rochelle Salt Bath 150°F	N/A
Plating Solutions, Copper Plating (Misc): Copper (Electroless)	N/A
Plating Solutions, Copper Plating (Misc): Copper Pyrophosphate	N/A
Plating Solutions, Gold Plating: Acid 75°F	N/A
Plating Solutions, Gold Plating: Cyanide 150°F	N/A
Plating Solutions, Gold Plating: Neutral 75°F	N/A
Plating Solutions, Indium Sulfamate Plating R.T.	N/A
Plating Solutions, Iron Plating: Ferrous Am Sulfate Bath 150°F	N/A
Plating Solutions, Iron Plating: Ferrous Chloride Bath 190°F	N/A
Plating Solutions, Iron Plating: Ferrous Sulfate Bath 150°F	N/A
Plating Solutions, Iron Plating: Sulfamate 140°F	N/A
Plating Solutions, Iron Plating: Sulfate- Chloride Bath 160°F	N/A
Plating Solutions, Iron Plating: Fluoborate Bath 145°F	N/A
Plating Solutions, Lead Fluoborate Plating	N/A
Plating Solutions, Nickel Plating: Electroless 200°F	N/A
Plating Solutions, Nickel Plating: Fluoborate 100-170°F	N/A
Plating Solutions, Nickel Plating: High- Chloride 130-160°F	N/A
Plating Solutions, Nickel Plating: Sulfamate 100-140°F	N/A
Plating Solutions, Nickel Plating: Watts Type 115-160°F	N/A
Plating Solutions, Rhodium Plating 120°F	A - Excellent
Plating Solutions, Silver Plating 80- 120°F	A - Excellent
Plating Solutions, Tin-Fluoborate Plating 100°F	N/A
Plating Solutions, Tin-Lead Plating 100°F	N/A
Plating Solutions, Zinc Plating: Acid Chloride 140°F	N/A
Plating Solutions, Zinc Plating: Acid Fluoborate Bath R.T.	N/A
Plating Solutions, Zinc Plating: Acid Sulfate Bath 150°F	N/A
Plating Solutions, Zinc Plating: Alkaline Cyanide Bath R.T.	N/A
Potash (Potassium Carbonate)	A ¹ - Excellent
Potassium Bicarbonate	A - Excellent

CHEMICAL	COMPATIBILITY
Potassium Bromide	A ¹ - Excellent
Potassium Chlorate	A ¹ - Excellent
Potassium Chloride	A ¹ - Excellent
Potassium Chromate	A ² - Excellent
Potassium Cyanide Solutions	A ¹ - Excellent
Potassium Dichromate	A ¹ - Excellent
Potassium Ferricyanide	A - Excellent
Potassium Ferrocyanide	A - Excellent
Potassium Hydroxide (Caustic Potash)	A ² - Excellent
Potassium Hypochlorite	A ¹ - Excellent
Potassium Iodide	A - Excellent
Potassium Nitrate	A - Excellent
Potassium Oxalate	N/A
Potassium Permanganate	A - Excellent
Potassium Sulfate	A ¹ - Excellent
Potassium Sulfide	A - Excellent
Propane (liquefied)	D - Poor
Propylene	D - Poor
Propylene Glycol	A - Excellent
Pyridine	B - Good
Pyrogalllic Acid	B - Good
Resorcinal	B ¹ - Good
Rosins	N/A
Rum	A - Excellent
Rust Inhibitors	N/A
Salad Dressings	N/A
Salicylic Acid	A - Excellent
Salt Brine (NaCl saturated)	A - Excellent
Sea Water	A ² - Excellent
Shellac (Bleached)	A ² - Excellent
Shellac (Orange)	A - Excellent
Silicone	A - Excellent
Silver Bromide	N/A
Silver Nitrate	A - Excellent
Soap Solutions	A - Excellent
Soda Ash (see Sodium Carbonate)	A ² - Excellent
Sodium Acetate	A - Excellent
Sodium Aluminate	A - Excellent
Sodium Benzoate	A - Excellent
Sodium Bicarbonate	A ² - Excellent
Sodium Bisulfate	A ² - Excellent
Sodium Bisulfite	A ² - Excellent
Sodium Borate (Borax)	A - Excellent

CHEMICAL	COMPATIBILITY
Sodium Bromide	A - Excellent
Sodium Carbonate	A ² - Excellent
Sodium Chlorate	A - Excellent
Sodium Chloride	A - Excellent
Sodium Chromate	N/A
Sodium Cyanide	A ² - Excellent
Sodium Ferrocyanide	A - Excellent
Sodium Fluoride	A - Excellent
Sodium Hydrosulfite	B - Good
Sodium Hydroxide (20%)	B - Good
Sodium Hydroxide (50%)	B ¹ - Good
Sodium Hydroxide (80%)	B ¹ - Good
Sodium Hypochlorite (<20%)	B - Good
Sodium Hypochlorite (100%)	B ¹ - Good
Sodium Hyposulfate	N/A
Sodium Metaphosphate	A - Excellent
Sodium Metasilicate	A ¹ - Excellent
Sodium Nitrate	A - Excellent
Sodium Perborate	A - Excellent
Sodium Peroxide	A - Excellent
Sodium Polyphosphate	A - Excellent
Sodium Silicate	A - Excellent
Sodium Sulfate	A - Excellent
Sodium Sulfide	A ² - Excellent
Sodium Sulfite	A - Excellent
Sodium Tetraborate	A - Excellent
Sodium Thiosulfate (hypo)	A ² - Excellent
Sorghum	N/A
Soy Sauce	N/A
Stannic Chloride	A - Excellent
Stannic Fluoborate	N/A
Stannous Chloride	C - Fair
Starch	A - Excellent
Stearic Acid	B - Good
Stoddard Solvent	D - Poor
Styrene	D - Poor
Sugar (Liquids)	A - Excellent
Sulfate (Liquors)	A - Excellent
Sulfur Chloride	D - Poor
Sulfur Dioxide	A ² - Excellent
Sulfur Dioxide (dry)	A ² - Excellent
Sulfur Hexafluoride	B - Good
Sulfur Trioxide	C ² - Fair
Sulfur Trioxide (dry)	C ¹ - Fair
Sulfuric Acid (<10%)	A - Excellent

CHEMICAL	COMPATIBILITY
Sulfuric Acid (10-75%)	B ² - Good
Sulfuric Acid (75-100%)	B ¹ - Good
Sulfuric Acid (cold concentrated)	C - Fair
Sulfuric Acid (hot concentrated)	D - Poor
Sulfurous Acid	B - Good
Sulfuryl Chloride	N/A
Tallow	A - Excellent
Tannic Acid	A - Excellent
Tanning Liquors	B - Good
Tartaric Acid	B - Good
Tetrachloroethane	D - Poor
Tetrachloroethylene	D - Poor
Tetrahydrofuran	D - Poor
Tin Salts	B - Good
Toluene (Toluol)	D - Poor
Tomato Juice	A - Excellent
Trichloroacetic Acid	B - Good
Trichloroethane	D - Poor
Trichloroethylene	D - Poor
Trichloropropane	N/A
Tricresylphosphate	A - Excellent
Triethylamine	A - Excellent
Trisodium Phosphate	A - Excellent
Turpentine	D - Poor
Urea	A - Excellent
Uric Acid	N/A
Urine	A ¹ - Excellent
Varnish	D - Poor
Vegetable Juice	A - Excellent
Vinegar	A - Excellent
Vinyl Acetate	B ² - Good
Vinyl Chloride	C - Fair
Water, Acid, Mine	A - Excellent
Water, Deionized	A ¹ - Excellent
Water, Distilled	A - Excellent
Water, Fresh	A - Excellent
Water, Salt	A - Excellent
Weed Killers	N/A
Whey	N/A
Whiskey & Wines	A - Excellent
White Liquor (Pulp Mill)	N/A
White Water (Paper Mill)	N/A
Xylene	D - Poor
Zinc Chloride	A - Excellent
Zinc Hydrosulfite	A - Excellent
Zinc Sulfate	A - Excellent

Ratings - Chemical Effect

A - Excellent

B - Good: Minor Effect, slight corrosion, or discoloration.

C - Fair: Moderate Effect, not recommended for continuous use. Softening or loss of strength, and swelling may occur.

D - Severe Effect: Not recommended for any use.

E - Information not available.

Explanation of Footnotes

1-Satisfactory to 72°F (22°C)

2-Satisfactory to 120°F (48°C)

The data contained herein is a compilation of existing published data from leading manufacturers of polyurethane and does not represent actual testing performed by UltraTech International, Inc.

This listing is offered only as a guide and utilizes information which, to the best of UltraTech's knowledge, is accurate and reliable. Due to variables and conditions of application beyond the control of UltraTech, none of the data shown in this guide is to be construed as a guarantee, expressed or implied. UltraTech International, Inc. assumes no responsibility, obligation or liability in conjunction with the use or misuse of the information herein.